

SECTION 1030 -- LIQUID ASPHALTS

1030.01 -- Description

AASHTO Rapid-Curing Cut-back Asphalt is the accepted NDR liquid asphalt.

1030.02 -- Material Characteristics

Cut-back asphalts shall conform to the AASHTO M 81, Rapid Curing Type requirements.

1030.03 -- Procedures

1. Storage tanks, transfer lines, and loading facilities for liquid asphaltic materials shall conform to the requirements of Subsection 1029.03, Paragraph 1. Liquid asphaltic materials offered for testing, in storage or at the time of loading, shall not exceed the temperature limits shown in Table 1030.01.

Table 1030.01

Maximum Storage Temperature		
Type	Grade	Degrees Fahrenheit (Maximum)
MC	30	175
MC, RC	70	250
MC, RC	250	275
MC, RC	800	300
MC, RC	3000	330

(These limits are higher than permissible application temperatures. See Division 500 for application temperature limits.)

2. All tank cars and tank trucks used for shipment of liquid asphaltic materials and the producer's or supplier's storage and heating provisions for these materials shall conform to the requirements of Subsection 1029.03, Paragraph 2.

1030.04 -- Acceptance Requirements

Liquid asphalts will be accepted as prescribed in the NDR *Materials Sampling Guide*.