

## **SECTION 1055 -- SHEET LEAD**

### **1055.01 -- Description**

Sheet lead shall conform to the requirements of ASTM B 29 for chemical copper lead. The lead sheet shall be of uniform thickness and shall be free from cracks, seams, slivers, scale, and other defects. Unless otherwise specified, lead sheet shall be 1/8 inch in thickness with a permissible tolerance of 1/32 inch.

### **1055.02 -- Acceptance Requirements**

Sheet lead will be accepted based on requirements of this Section and sampling and testing requirements in accordance with the NDR *Materials Sampling Guide*.

## **SECTION 1056 – STEEL SHEET PILES AND SHEET PILE CORNERS**

### **1056.01 -- Description**

1. Steel sheet piles and steel sheet pile corners shall conform to the requirements of ASTM A 328/A 328M.

2. All steel sheet piling shall be of the style, dimensions, and weight specified in the plans.

### **1056.02 -- Acceptance Requirements**

Steel sheet piles and sheet pile corners will be accepted based on requirements of this Section and sampling and testing requirements in accordance with the NDR *Materials Sampling Guide*.